1-800-637-3739

MASTERFLEX®

Choosing the Right Masterflex® Tubing Formulation

			A	pplicat	ion su	uitabil	ity†					
Pump tubing formulation	Advantages	Acids	Alkalies	Organic solvents	Pressure	Vacuum	Viscous	Sterile fluids	Meets classifications	Gas permeability	Sterilization	
Silicone (platinum-cured)	Excellent biocompatibility. No leachable additives, DOP, or plasticizers; bhthalate and latex-free: odorless and nontoxic.	N/R	N/R		F	G	F	E	USP Class V Extractables Exceeds Class VI Implant European Pharmacopoeia (EP 3.1.9)	00 - 00 100		
96410-, 96510-series	fungus-resistant. No taste imparted to transported fluids.								FDA 21 CFR 177.2600; FDA 21 CFR 210 and 211; Exceeds 3A sanitary cGMPs;	CO ₂ : 20,132 H ₂ : 6579 O ₂ : 7961	Sterilize by EtO, autoclave, or	
Masterflex PUMP	Weather, ozone, corona, and radiation resistant. Minimal tendency to take a set. Translucent, clear to light amber.	Temperature range: Static: -50 to 230°C (-58 to 446°F) Dynamic (pumping): -40 to 100°C (-40 to 212°F)							REACH (non-DEHP) compliant RoHS compliant ADCF compliant	N ₂ : 2763	gamma irradiation.	
Silicone (peroxide-cured)	Excellent biocompatibility. No additives, plasticizers or DOP; odorless	N/R	N/R	N/R	F	G	F	E	USP Class VI European Pharmacopoeia (EP 3.1.9)		Sterilize by EtO or autoclave.	
96400-, 96406-series	and nontoxic, fungus-resistant. No taste imparted to transported fluids.								FDA 21 CFR 177.2600 Exceeds 3A sanitary standards REACH (non-DEHP) compliant ROHS compliant ADCF compliant	CO ₂ : 20,132 H ₂ : 6579		
Masterflex PUMP	Weather, ozone, corona, and radiation resistant. Minimal tendency to take a set. Translucent, clear to light amber.	Sta Dy	atic: -{ /namic	re ranç 50 to 2 (pump 212°F	30°C oing): -					0 ₂ : 7961 N ₂ : 2763		
BioPharm Silicone (platinum-cured)	Ultra-smooth inner surface minimizes particle entrapment. Lower absorption; excellent biocompatibility;	N/R	N/R	N/R	F	G	F	E	USP Class VI European Pharmacopoeia (EP 3.1.9)	CO ₂ : 25,147 H ₂ : — O ₂ : 4715 N ₂ : 2284	Sterilize by EtO, autoclave, or gamma irradiation.	
96420-, 96421-series Masterflex PUMP	no leachable additive, DOP, or plasticizers. Very low extractables. Odorless and nontoxic, fungus-resistant. No taste imparted to transported fluids. Weather, ozone, corona, and radiation resistant.	Sta Dy	atic: –6 /namic	re rang 60 to 2 (pump	, 32°C oing): -				FDA 21 CFR 177.2600 Exceeds 3A sanitary standards REACH (non-DEHP) compliant ROHS compliant			
	Translucent, clear to light amber.	(-	-40 to	212°F)			I				
BioPharm Plus Silicone (platinum-cured)	Similar to BioPharm Silicone, plus: Longest life of any silicone pump tubing. Lower spallation than regular silicone. Enhanced pressure capability. Fungus-resistant.	N/R	N/R	N/R	F	G	F	E	USP Class VI	CO - 25 147		
96440-, 96441-series									European Pharmacopoeia (EP 3.1.9) FDA 21 CFR 177.2600 Exceeds 3A sanitary standards	CO ₂ : 25,147 H ₂ : — O ₂ : 4715	Sterilize by Et0, autoclave, or	
Masterflex PUMP	No. 1. Co. on to a both to also Pateria.	Temperature range: Static: -60 to 232°C (-75 to 450°F) Dynamic (pumping): -40 to 100°C (-40 to 212°F)							REACH (non-DEHP) compliant RoHS compliant	N ₂ : 2284	gamma irradiation.	
Puri-Flex™	Biocompatible. Heat sealable and weldable.	G	G	N/R	G	G	Е	Е	USP Class VI	CO ₂ : 1200 H ₂ : — O ₂ : 200 N ₂ : 80	Sterilize by EtO, autoclave up to 135°C (275°F), gamma irradiation up to 4.5 Mrad.	
96419-series	Long pump life when compared to silicone or other TPE tubings. Low spallation when compared to silicone								FDA 21 CFR 177.2600 and 177.1810			
Masterflex PUMP		Sta	atic: -{ /namic	re ranç 50 to 1 (pump 212°F	35°C (ina): -				REACH (non-DEHP) compliant ROHS compliant ADCF compliant			
C-Flex®	Physical properties similar to silicone	G	G	N/R	F	G	F	E	UCD Class VI	CO ₂ : — H ₂ : — O ₂ : 150		
06424-series	with chemical compatibility of Tygon®. Inexpensive.								USP Class VI European Pharmacopoeia (EP 3.2.9) REACH (non-DEHP) compliant		Sterilize by EtO,	
MasterHex" PUMP	Riocompatible	Sta Dy	atic: –4 /namic	re ranç 45 to 1 (pump 212°F	21°C oing): -				REACH (non-dehr) compliant RoHS compliant ADCF compliant	0 ₂ : 150 N ₂ : —	autoclave, or gamma irradiation.	
C-Flex® ULTRA	Physical properties similar to silicone with chemical compatibility of Tygon®.	G	G	N/R	F	G	F	E	USP Class VI	00.01	Sterilize by gamma	
06434-series	Biocompatible. Heat sealable and weldable. Longer pump life and lower spallation than C-Flex. Translucent.	Sta	Temperature range: Static: -45 to 121°C (-50 to 250°F) Dynamic (pumping): -40 to 100°C						Curopean Pharmacopoeia (EP 3.2.9) REACH (non-DEHP) compliant ROHS compliant ADCF compliant	CO ₂ : 2.1 H ₂ : — O ₂ : 1.1 N ₂ : 3.4	irradiation or one cycle of autoclave at 121°C (250°F), 1 bar (15 psi) for 30 minutes.	
				212°F		10 10						

Choosing the Right Masterflex® Tubing Formulation (continued)

orioooning	the hight Master	110					_			itinueu)	
Bound Man		Application suitability†								0	
Pump tubing formulation	Advantages	Acids	Alkalies	Organic solvents	Pressure	Vacuum	Viscous fluids	Sterile fluids	Meets classifications	Gas permeability	Sterilization
PharMed® BPT	Great for tissue and cell work—nontoxic and nonhemolytic. Long service life (up to 10,000 hrs);	G	G	N/R	G	G	E	E			
06508-series	reduces tubing costs and pump downtime. Opaque to UV and visible light to protect light-sensitive fluids.								USP Class VI European Pharmacopoeia (EP 3.2.9) REACH (non-DEHP) compliant	CO ₂ : 1200 H ₂ : — O ₂ : 200	Sterilize by EtO, autoclave, or gamma irradiation
MASTERFLEX PUMP	Low gas permeability. High-pressure 10.3 bar (150 psi) version available. Opaque, beige	Temperature range: Static: -51 to 132°C (-60 to 270°F) Dynamic (pumping): -20 to 100°C (-4 to 212°F)							RoHS compliant	N ₂ : 80	up to 2.5 Mrad.
GORE® STA-PURE® pump tubing	Unique composite structure adds strength and flex durability. Greater security against rupture up to 100 psig*.	N/R	N/R	N/R	E	G	G	E	USP Class VI		
Series PCS (96241-)			USP <87> USP Physicochemical Tests Compliant with restricted							_	Sterilize by autoclave or SIP
	Consistent flow rate over long duration of use. Withstands rigors of CIP/SIP processing.			ire ranç Cole-Pa					substances per REACH and RoHS No raw materials of animal origin		(steam in place).
GORE® STA-PURE® pump tubing	Unique composite structure adds strength and flex durability. Greater chemical resistance than Series PCS.	Е	E	E	E	G	G	E	USP Class VI	_	Sterilize by autoclave or SIP (steam in place).
Series PFL (96242-)									USP <87> USP Physicochemical Tests Compliant with restricted		
	Stable flow rates achievable to 60 psig*. Withstands rigors of CIP/SIP processing.			ire ranç Cole-Pa					substances per REACH and RoHS No raw materials of animal origin		
PharmaPure®	Nontoxic and nonhemolytic (similar to PharMed® BPT); biocompatible.	G	G	N/R	G	G	E	E			
06435-series	Long life even under pressure; up to 1000 hours at 2.7 bar (40 psi).								USP Class VI FDA 21 CFR 177.2600 European Pharmacopoeia (EP 3.2.9)	CO ₂ : 1200 H ₂ : — O ₂ : 200	Sterilize by EtO, autoclave or gamma irradiation
MASTERFLEX PUMP	Low extractables. Low gas permeability. Opaque, off-white.	Temperature range: Static: -51 to 132°C (-60 to 270°F) Dynamic (pumping): -20 to 100°C (-4 to 212°F)							REACH (non-DEHP) compliant RoHS Compliant	N ₂ : 80	up to 2.5 Mrad.
Chem-Durance® Bio	Excellent chemical resistance.	Е	E	G	Е	Е	E	E			
06442-series	Excellent life and durability under pressure. Low spallation. Plasticizer-free inner liner.								USP Class VI FDA 21 CFR 177.2600 REACH (non-DEHP) compliant	CO ₂ : 745 H ₂ : — O ₂ : 200	Sterilize by EtO, autoclave or
Masterflex PUMP	High dielectric constant. Excellent biocompatibility. Opaque, beige.	Sta Dyr	tic: –6	ire rang 60 to 74 (pump 04°F)	4°C (−				RoHS Compliant	N ₂ : 80	gamma irradiation.
PTFE	Chemically inert. Excellent chemical resistance. Will not leach into or absorb out of fluid being pumped. Extremely low gas permeability.	Е	E	E	G	G	E	G			
77390-series		_	USP Class VI REACH (non-DEHP) co RoHS compliant					REACH (non-DEHP) compliant	CO ₂ : 6.8 H ₂ : —	Sterilize by EtO or autoclave.	
	Nontoxic. Virtually nonporous. Low coefficient of friction. Translucent, white.	Sta Dyr	itic: –2 namic	re rang 240 to 2 (pump 302°F)	260°C ing): –			l°F)	ADCF compliant	O ₂ : — N ₂ : 1.0	altonaro.
Tygon® E-LFL	Longest life of all Tygon® peristaltic tubing. Clear for easy flow monitoring. Broad chemical resistance.	G	G	N/R	G	G	E	G	USP Class VI European Pharmacopia (EP 3.2.9)	CO ₂ : 563	
06440-series	Nonaging, nonoxidizing. Low gas permeability. Smooth bore.	Temperature range:							FDA 21 CFR 175.300 EU Food REACH (non-DEHP) compliant	H ₂ : — O ₂ : 124	Sterilize by EtO or autoclave.
MASTERHEX PUMP	Good for viscous fluids. High dielectric constant. Transparent, clear.	Sta Dyr	tic: -4	16 to 74 (pump	4°C (–				RoHS compliant ADCF compliant	N ₂ : 67	

[†]E = Excellent, G = Good, F = Fair, P = Poor, N/R = not recommended

^{*}Actual performance depends on the specific application conditions.

Choosing the Right Masterflex® Tubing Formulation (continued)

<u> </u>	the rught mastern			pplica					<u> </u>		
Pump tubing formulation	Advantages	Acids	Alkalies	Organic solvents		Vacuum	Viscous	Sterile fluids	Meets classifications	Gas permeability	Sterilization
Tygon® E-Food (B-44-4X)	Designed especially for handling food products. Bore is extremely smooth (better than most stainless steels)	G	G	N/R	G	G	E	F	FDA 21 CFR 175.300 EU Food NSF-51 REACH (non-DEHP) compliant ROHS compliant ADCF compliant Meets 3A sanitary standards	CO ₂ : 270 H ₂ : 97 O ₂ : 60 N ₂ : 30	Sterilize by Et0 or autoclave.
Masterflex PUMP	Nontoxic, will not affect taste or odor, and clear for CIP and flow verification. Excellent nonwetting properties permit flush cleaning and complete drainage. High dielectric constant. Transparent, clear.	Sta Dyı	itic: –3	re rang 66 to 74 (pump 04°F)	4°C (–						
Tygon® E-Lab (E-3603) 06509-series	Inexpensive tubing for general laboratory applications. Clear for easy flow monitoring. Handles virtually all inorganic chemicals.	G	G	N/R	G	G	E	Р	USP Class VI FDA 21 CFR 175.300 EU Food NSF-51 REACH (non-DEHP) compliant ROHS compliant ADCF compliant	CO ₂ : 360 H ₂ : 97 O ₂ : 80 N ₂ : 40	Sterilize by EtO or autoclave.
Masterflex PUMP	Nonaging, nonoxidizing. Low gas permeability. Good for viscous fluids. High dielectric constant. Transparent, clear.	Sta Dy	atic: – namic	re rang 46 to 7 (pump (04°F)	4°C (-						
Versilon™ Chemical (2001) 06475-series	Best chemical resistance of any Tygon® formulation. Compatible with many polar solvents. Plasticizer-free.	E	E	G	G	G	E	G	FDA 21 CFR 175.300 REACH (non-DEHP) compliant ROHS compliant ADCF compliant	CO ₂ : 114 H ₂ : — O ₂ : 19 N ₂ : 9	Sterilize by EtO, autoclave, or gamma irradiation.
Masterflex PUMP	Clear for easy flow monitoring. Low extractability. Low gas permeability. High dielectric constant. Transparent, clear.	Sta Dy	atic: –	re rang 77 to 5 (pump 104°F)	7°C (-			F)			
Tygon® Fuel & Lubricant (F-4040-A) 06401-series	Specially formulated to transport hydrocarbons, petroleum products, and distillates. Suitable for gasoline, kerosene, heating oils, cutting fluids, and glycol-based coolants.	G	G	N/R	G	G	E	Р	REACH (non-DEHP) compliant RoHS compliant ADCF compliant	CO ₂ : 100 H ₂ : 97 O ₂ : 22 N ₂ : 12	Sterilization is not recommended.
Masterflex PUMP	Minimum extractability. Low gas permeability. High dielectric constant. Transparent, yellow.	Sta Dyi	itic: –3	re rang 7 to 7 (pump 04°F)	4°C (−						
Versilon ™ (A-60-G) 06404-series	Best choice for vacuum/pressure applications. Offers longest pump tubing life. Heat, ambient ozone resistant. Good resistance to acids/alkalies.	G	G	N/R	E	Е	E	N/R	NSF-51 REACH (non-DEHP) compliant RoHS compliant	CO ₂ : 1200 H ₂ : — O ₂ : 200 N ₂ : 80	Sterilize by EtO, autoclave, or gamma irradiation.
MASTERFIEX PUMP	Black color hides dirt and dust. Heat sealable, nonaging, and nonoxidizing. High dielectric constant. High-pressure version available. Opaque, black.	Sta Dyi	itic: –5	re rang i9 to 13 (pump 12°F)	32°C (· ·)			
Versilon™ (A-60-F)	Similar to Norprene® but with FDA approval. Excellent for food/dairy applications. Longest life, good flow consistency.	G	G	N/R	E	Е	E	G	FDA 21 CFR 177.2600 NSF-51 REACH (non-DEHP) compliant RoHS compliant	CO ₂ : 1200 H ₂ : — O ₂ : 200 N ₂ : 80	Sterilize by EtO, autoclave, or gamma irradiation.
MASTERFLEX PUMP	Heat and ozone resistant. Good resistance to acids/alkalies. Heat sealable, nonaging, and nonoxidizing. High dielectric constant. Opaque, beige.	Sta Dyi	itic: –5	re rang i9 to 1: (pump 12°F)	32°C (–60 to	270°F 100°C	(i)			
Viton®	Perfect for food and lab applications where FDA compliance is required.	Е	Е	Variable—test before using	G	G	G	F		CO ₂ : 76 to 79	
96412-series Masterflex PUMP	Excellent chemical resistance. Resistant to corrosives, solvents, and oils at elevated temperatures. Low gas permeability. Opaque, black.	Sta Dyı	itic: –3	re rang 2 to 20 (pump	ge: 05°C (<u> </u>	FDA 21 CFR 177.2600 ADCF compliant	CO ₂ : 76 to 79 H ₂ : — O ₂ : 13 to 15 N ₂ : 4.3	Sterilization is not recommended.

[†]E = Excellent, G = Good, F = Fair, P = Poor, N/R = not recommended